Picture	Model No.	Color	Surface Curing Time	Hardness	Tensile Strength	Elongation at break	Temperature Range	Density	Dielectric strength	Volume resistivity
	TN368	Black	5-25 minutes	35+/-5 HsA	≥1.5Mpa	⩾200%	-50C to 280C	None	None	None
	SMG533	Black	5-30 minutes	42-55	≥2.0Mpa	⩾250%	None	1.4-1.5g/cm3	⩾15KV/mm	⩾$1x10^{14}$Ω.cm
	TBL-6237	Grey	⩽20 minutes	40+/-5 HsA	≥1.5Mpa	⩾300%	-40C to 180C	None	⩾15KV/mm	⩾$1x10^{14}$Ω.cm
	172	Black	None	None	None	None	-50C to 150C	None	None	None
	None	Black	None	None	None	None	None	None	None	None